

L.P. Bader & Co. GmbH
Neckartal 140 D-78628 Rottweil
☒ Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
Internet: www.lubaprint.de

LUBA-print Wax Dispersion 161/P

Application field:

Solvent - containing varnishes and printing inks,
improve slip property.

Processing information:

2 - 6 % of this wax dispersion to be added to the lacquer or printing ink while stirring.
Extreme temperature changes affect the particle size distribution. The wax can become dissolved in part at temperatures > 35°C and can crystallize uncontrolled at lower temperatures.

Technical data:

Unit:

Method:

Solid:	min:	28,5 %	Sartorius MA 100 infrared drier
	max:	31,5 %	
Melting range:	min:	86 °C	DSC (solid wax)
	max:	92 °C	
Solvent:		Ethanol	
Density:	min:	0,81 g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	0,83 g/ccm	
Viscosity:	min:	10 mPa.s	Rheolab MC1 DIN 53019 1.291s-1
	max:	40 mPa.s	

fineness: measurement not applicable

Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.
Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.