

L.P. Bader & Co. GmbH
Neckartal 140 D-78628 Rottweil
☒ Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
Internet: www.lubaprint.de

LUBA-print Wax Dispersion 103/A-neu

Application field:

To improve the sandability

Processing information:

2 - 6 % of this wax dispersion to be added to the lacquer while stirring

| <u>Technical data:</u> | <u>Unit:</u> | <u>Method:</u> |
|------------------------|------------------------------------|-----------------------------------|
| Solid: | min: 23,0 % max: 25,0 % | Sartorius MA 100 infrared drier |
| | Zinc soap | |
| Melting range: | min: 121 °C max: 127 °C | DSC (solid wax) |
| Solvent: | n-Butyl Acetate | |
| Particle size 50%: | min: 3,5 µm max: 4,5 µm | Picture-Particle-Analyzing-System |
| Fineness 98% <: | 10,0 µm | Picture-Particle-Analyzing-System |
| Density: | min: 0,93 g/ccm max: 0,95 g/ccm | Pyknometer DIN EN ISO 2811-1 |
| Viscosity: | min: 20 mPa.s max: 60 mPa.s | Rheolab MC1 DIN 53019 1.291s-1 |

Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.
Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.