

L.P. Bader & Co. GmbH
Neckartal 140 ▲ D-78628 Rottweil
☒ Postfach 1137 ▲ D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
Internet: www.lubaprint.de

LUBA-print Wax Dispersion 246/D 3

Application field:

metallic-paints (base-coat):
improve thixotropy and fixation.

Processing information:

base - coat : approximately 10 % to be added
Stir before use.
EVA - copolymer dispersions have the tendency to build up agglomerates.

Technical data:

Unit:

Method:

Solid:	min:	10,5 %	Sartorius MA 100 infrared drier
	max:	12,5 %	
Melting range:	min:	93 °C	DSC (solid wax)
	max:	103 °C	
Solvent:		n-Butylacetate / Iso Butanol in a ratio 90:10	
Density:	min:	0,87 g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	0,89 g/ccm	
Viscosity:	min:	20 mPa.s	Rheolab MC1 DIN 53019 1.291s-1
	max:	45 mPa.s	

fineness: measurement not applicable

Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.