

L.P. Bader & Co. GmbH
Neckartal 140 D-78628 Rottweil
☒ Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
Internet: www.lubaprint.de

LUBA-print Wax Dispersion 425/H

Application field:

Direct natural surface coating for wood and cork,
to improve hydrophoby

Processing information:

Can be applied by hot spraying or brushing directly or diluted with wax dispersion LUBA-print 459 (Paraffin) or 887/K (carnauba wax) on the surface. Drying approx. after 24 hours, final hardness after 2 - 4 weeks.

Technical data:

Unit:

Method:

Solid:	min:	4,5	%	calculated
	max:	5,5	%	
		100 % Combination of natural oil and natural wax part of wax is approx. 5%		
Melting range:	min:	87	°C	DSC (solid wax)
	max:	93	°C	
Density:	min:	0,95	g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	0,97	g/ccm	
Viscosity:		pasty		

fineness: measurement not applicable

Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.
Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.