

L.P. Bader & Co. GmbH
Neckartal 140 D-78628 Rottweil
☒ Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
Internet: www.lubaprint.de

LUBA-print Wax Dispersion VP 646/H

Application field:

UV-lacquers:
for matting effects and to improve mar resistance.

UV-printing inks:
to improve rub resistance.

Processing information:

5 - 20 % of this wax dispersion to be added to the lacquer or the printing ink while stirring

Technical data:

Unit:

Method:

Solid:	min:	35,0 %	calculated
	max:	37,0 %	
		org. Matting Agent/ PE	
Melting range:	min:	115 °C	DSC (solid wax)
	max:	121 °C	
Solvent:		Propoxylated (2) Neopentyl Glycol Diacrylate	
Particle size 50%:	min:	5,0 µm	Picture-Particle-Analyzing-System
	max:	7,0 µm	
Fineness 98% <:		19,0 µm	Picture-Particle-Analyzing-System
Density:	min:	1,00 g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	1,02 g/ccm	

Experimental product: Temporary data, final limits can be given after 5 produced batches.

Storage:

In original closed containers lasting at least 6 months at temperatures between 5-35°C.
Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.