

L.P. Bader & Co. GmbH  
Neckartal 140   ▲ D-78628 Rottweil  
☒ Postfach 1137   ▲ D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0  
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: [service@lubaprint.de](mailto:service@lubaprint.de)  
Internet: [www.lubaprint.de](http://www.lubaprint.de)

## LUBA-print Wax Dispersion T-152/D30

### Application field:

Solvent-based paints:  
to improve slip property and water proofing of wood surfaces.

### Processing information:

2 - 6 % of this wax dispersion to be added to the lacquer or application directly on the wood as water proofing agent

### Technical data:

### Unit:

### Method:

Solid:	min:	18,5 %	Sartorius MA 100 infrared drier
	max:	21,5 %	
Polyethylene-Wax / microcryst. Wax			
Drop point:	min:	98 °C	DIN ISO 2176 (solid wax)
	max:	106 °C	
Solvent:		Dearomatized Hydrocarbon Boiling Range 140-170°C	
Density:	min:	0,76 g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	0,78 g/ccm	
Viscosity:	min:	8 mPa.s	Rheolab MC1 DIN 53019 1.291s-1
	max:	35 mPa.s	

fineness: conditional on temperature

### Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.  
Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.