

L.P. Bader & Co. GmbH  
Neckartal 140    D-78628 Rottweil  
☒ Postfach 1137    D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0  
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: [service@lubaprint.de](mailto:service@lubaprint.de)  
Internet: [www.lubaprint.de](http://www.lubaprint.de)

## LUBA-print Wax Dispersion VP 460/D

### Application field:

For waterbased systems to improve sandability.

### Processing information:

2 - 8 % of this wax dispersion to be added to the lacquer or the paint while stirring.

### Technical data:

### Unit:

### Method:

Solid:	min:	48,0 %	Sartorius MA 100 infrared drier
	max:	52,0 %	
		Calciumstearate	
Solvent:		Water	
Emulsifier-system:		non - ionic / anionic	
pH-Value:	min:	10,0	DIN ISO 976
	max:	12,5	
Density:	min:	1,01 g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	1,03 g/ccm	
Viscosity:	typ.:	110 mPa.s	Rheolab MC1 DIN 53019 1.291s-1

Experimental product: Temporary data, final limits can be given after 5 produced batches.

### Storage:

In original closed containers lasting at least 6 months at temperatures between 5-35°C.  
Stir well before use!

Protect from frost!

After long storage, particularly after usage of some of the product, evaporation of water is possible and visible signs of particles may be present.

We therefore recommend filtration of the product before use.

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.