

L.P. Bader & Co. GmbH
Neckartal 140 D-78628 Rottweil
☒ Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
Internet: www.lubaprint.de

LUBA-print Wax Dispersion 715/A

Application field:

Metal paints:
to improve slip property.

metallic-paints (base-coat):
to improve thixotropy and fixation.

Processing information:

1. 2 - 6 % of this wax dispersion to be added to the paint while stirring
base - coat: 10 % to be added
2. The well stirred wax dispersion should be added approximately 15 - 25% to the
binder by using a dissolver until a homogenous mixture is reached.
The other rawmaterials should be slowly added by stirring
Stir before use, EAA- copolymer dispersions have the tendency to build up
agglomerates

Technical data:

Unit:

Method:

Solid:	min:	10,5 %	Sartorius MA 100 infrared drier
	max:	12,5 %	
Melting range:		EAA - Copolymer	DSC (solid wax)
	min:	102 °C	
	max:	108 °C	
Solvent:		Xylene / n-Butyl Acetate / Isobutanol in a ratio 40:41:9	
Density:	min:	0,87 g/ccm	Pyknometer DIN EN ISO 2811-1
	max:	0,89 g/ccm	
Viscosity:	min:	15 mPa.s	Rheolab MC1 DIN 53019 1.291s-1
	max:	30 mPa.s	

fineness: measurement not applicable

Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.
Stir well before use!

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.