

L.P. Bader & Co. GmbH
Neckartal 140 D-78628 Rottweil
☒ Postfach 1137 D-78611 Rottweil

Telefon: + 49 (0)7 41-9 42 52-0
Telefax: + 49 (0)7 41-9 42 52-50

E-Mail: service@lubaprint.de
Internet: www.lubaprint.de

LUBA-print Wax Dispersion 205

Application field:

Water-based paint systems:
to improve surface hardness with good gloss stability.

Processing information:

2 - 6 % of this wax dispersion to be added to the paint while stirring

<u>Technical data:</u>	<u>Unit:</u>	<u>Method:</u>
Solid:	min: 34,0 % max: 36,0 %	Sartorius MA 100 infrared drier
	Polyethylene-Wax	
Melting range:	min: 125 °C max: 135 °C	DSC (solid wax)
Solvent:	Water	
Emulsifier-system:	non - ionic	
pH-Value:	min: 9,0 max: 10,0	DIN ISO 976
Fineness 98% <:	5,0 µm	Single pass test
Density:	min: 0,98 g/ccm max: 1,00 g/ccm	Pyknometer DIN EN ISO 2811-1
Viscosity:	min: 20 mPa.s max: 60 mPa.s	Rheolab MC1 DIN 53019 1.291s-1

Storage:

In original closed containers lasting at least 12 months at temperatures between 5-35°C.
Stir well before use!

Protect from frost!

After long storage, particularly after usage of some of the product, evaporation of water is possible and visible signs of particles may be present.

We therefore recommend filtration of the product before use.

The above mentioned information is derived from our quality checks. It does not relieve the purchaser from examining the product delivery and gives no assurance of suitability of the product for any particular purpose.